

## Water reducing/plasticizing admixture

### Description of Product

Pozzolith<sup>®</sup> 364 is a ready-to-use, high performance liquid admixture, which enables increased workability and water reduction to achieve a more consistent concrete.

Pozzolith<sup>®</sup> 364 complies with:

- BS 5075, Part 1
- EN 934 - 2

### Application

Pozzolith<sup>®</sup> 364 is supplied ready for use. The admixture should be added to the concrete mix at the same time as the water. Pozzolith<sup>®</sup> 364 should never be added directly to the cement. Pozzolith<sup>®</sup> 364 should not be used in conjunction with other admixtures without prior consultation with the BASF IBC Admixture Systems Technical Department.

### Features and Benefits

Concrete manufactured using Pozzolith<sup>®</sup> 364 should have the following benefits:

- Increased plasticity and workability.
- Increased strength - both compressive & flexural
- Reduced water content required for a given workability range.
- Increased durability to damage from freezing & thawing.
- Workability and set times can be extended by using Pozzolith<sup>®</sup> 364 at an increased dosage.

### Fields of Applications

Pozzolith<sup>®</sup> 364 is suitable for use in the following applications:

- Ready mixed concrete
- Pumped Concrete

## Technical Data/Typical Properties

Appearance	Dark Brown Liquid
Specific gravity @ 20°C	1.17 ± 0.01 g/cm <sup>3</sup>
pH	9.4
Chloride Ion Content	<0.02%
Freezing Point	- 10°C
Alkali Content (as equivalent Na <sub>2</sub> O)	2.7%

## Application Procedure

### Dosage Rate

Pozzolith<sup>®</sup> 364 admixture is recommended for use at a rate of 0.2 – 0.6 litres per 100 kg of cement for most concrete mixes using average concrete ingredients. Due to variations in site conditions and concrete materials, dosage rates other than those recommended may be required.

The manufacturer would advise that trial mixes should be undertaken, using job materials, in simulated job conditions to determine suitable dosage rates and performance.

### Over Dosage

Over-dosing using Pozzolith<sup>®</sup> 364 can cause the following effects:

- Considerable increases in workability
- Increased Air Entrainment
- Retardation of initial and final set

If over-dosing does occur please consult the BASF IBC Admixture Systems Technical Department for recommendations.

### Packaging

Pozzolith<sup>®</sup> 364 admixture is supplied in 25 Litre, 210 Litre, 1000 Litre containers and Bulk.

### Storage

Store away from direct sunlight in ambient temperatures and in dry conditions.

### Shelf life

12 months in manufacturers sealed drums.

### Watchpoints

If Pozzolith<sup>®</sup> 364 admixture has frozen, thaw at temperatures above 2°C and completely reconstitute by mild agitation. Do not use pressurised air for agitation.



The Chemical Company

# Pozzolith<sup>®</sup> 364

(Formerly Conplas 717)

BASF IBC Admixture Systems Limited,  
Unit 143 Baldoyle Industrial Estate,  
Baldoyle,  
Dublin 13, Ireland  
Tel: +353 (01) 832 1033  
Fax +353 (01) 839 3539  
www.admixturesystems.ie

Pozzolith<sup>®</sup> 364, BASF IBC Admixture Systems Limited, Version 1

#### Health and Safety

\*For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

The following general comments apply to all products.

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs, (which may also be tainted with vapour until the product is fully cured and dried). Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Keep away from children and animals. Reseal containers after use.

#### Spillage

Chemical products can cause damage; clean spillage immediately.

#### DISCLAIMER

"BASF IBC Admixture Systems Limited" (the Company) endeavours to ensure that advice and information given in Product Data Sheets, Method Statements and Material Safety Data Sheets (all known as Product Literature) is accurate and correct. However, the Company has no control over the selection of its products for particular applications. It is important that any prospective customer, user or specifier, satisfies him/her-self that the product is suitable for the specific application. In this process, due regard should be taken of the nature and composition of the background/base and the ambient conditions both at the time of laying/applying/installing the material and when the completed work is to be brought into use.

Accordingly, no liability will be accepted by the Company for the selection, by others, of a product, which is inappropriate to a particular application.

Products are sold subject to the Company's standard conditions of sale and all customers, users and specifiers, should ensure that they examine the Company's latest Product Literature.